
TECHNICAL DATA SHEET**87# Bleached Polycoated Kraft PE/2 S1S****Product Construction**

	Medium Release Silicone
	PE Coating
	64# Bleached Kraft
	PE Coating

Basis Weight	#/ream g/sqm	87 ± 5 141 ± 8
Caliper	Mils Microns	6.46 ± .4 164 ± 10
Color		Bleached
Tensile Strength – md	N/15mm	110 ± 40
Tear Strength – md	nN	950 ± 200
Mositure	%	5.5± 1
Roughness Backside(Bekk)	Sec	28 ± 10
Release	cN/25mm	14

The technical information in this form does not absolve the customer or end user from carrying out its own testing and sampling, particularly in respect of face/adhesive/liner interactions used in manufacturing and aging.

Recommended Storage and Rollstock Shelf Life:

Product as supplied in original packaging will maintain stated properties for a period of two (2) years from date stamped on shipping container when stored at temperatures of 50-80°F (10-27°C) and a relative humidity between 40-60 percent.

Please see reverse side for important product, safety and warranty information.

¹Conditions based on internal studies may not be representative of actual end use/performance and we recommend our OEM customers run their own studies using their device design.

² May require pre-treatment to increase ink anchorage before printing.