

#### December, 2017

# 3M<sup>™</sup> Adhesive Transfer Tape 463

#### **Product Description**

3M<sup>™</sup> Adhesive Transfer Tapes 463, 465, 9457, 9665 are made with 3M<sup>™</sup> Acrylic Adhesive 400 and are ideal for bonding together a wide variety of surfaces, including paper, cardboard, metals, glass, and HSE (high surface energy) plastics. This pressure sensitive acrylic adhesive family features excellent initial adhesion to HSE materials with good holding power at lower temperatures. 3M<sup>™</sup> Adhesive Transfer Tapes 463, 465 and 9665 contain discrete glass fibers to aid in processing and handling of the product, 3M<sup>™</sup> Adhesive Transfer Tape 9457 does not contain fibers.

This adhesive family offers constructions available in 1 mil and 2 mil thicknesses and provide a variety of liner configurations to help ensure optimum process flexibility.

#### **Product Features**

- Tapes meet the requirements of U.S. Government specification MIL-P-19834B, Type I.
- 3M<sup>™</sup> Adhesive Transfer Tape 463 is designed for use with 3M automatic dispensing equipment.



# 3M<sup>™</sup> Adhesive Transfer Tape 463

#### **Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

# **Typical Physical Properties**

Property	Values		Attribute Modifier	Notes
Adhesive Thickness	0.05 mm	2.0 mil		
Liner	60# Densified Kraft			
Liner Color	Tan, No Print		Primary	
Liner Thickness	0.09 mm	3.5 mil		The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.

# **Typical Performance Characteristics**

90° Peel Adhesion		Dwell/Cure Time	Dwell Time Units	Notes
1.6 N/cm		15	min	
15 oz/in		15	min	12 in/min (300 mm/min)
2.7 N/cm	25 oz/in	72	hr	12 in/min (300 mm/min)

Property: 90° Peel Adhesion Method: ASTM D3330 Temp C: 22C Temp F: 72F Environmental Condition: 52%RH Substrate: Stainless Steel Backing: 2 mil Aluminum Foil

# **Available Sizes**

Property	Values		Notes
Master Width	1219 mm	48 in	More sizes may be available. Please call 800- 362-3550 or talk to your local 3M representative for more information.

#### **Environmental Resistance**

Humidity Resistance: High humidity has a minimal effect on adhesive performance. Bond strength (is generally higher/shows no significant reduction) after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

UV Resistance: When properly applied, nameplates and decorative trim parts are not adversely affected by outdoor exposure.

Water Resistance: Immersion in water has no appreciable effect on the bond strength.

Chemical Resistance: When properly applied, parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.

Bond Build-up: The bond strength of 3M<sup>™</sup> Adhesive 400 increases as a function of time and temperature

Temperature/Heat Resistance: Adhesive 400 is usable for short periods (minutes, hours) at temperatures up to 250°F (120°C) and for intermittent longer periods (days, weeks) up to 150°F (65°C).

Lower Temperature Service Limit: -60F (-50°C).

# Handling/Application Information

#### **Application Ideas**

- High-speed flying splices on most grades of paper.
- Splicing of foils, films, fabrics.
- Laminating adhesive for foams, photos.
- Attaching metal or plastic nameplates.
- Mounting promotional items, posters.
- Core starting.

#### **Application Techniques**

• Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength.

• To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.\* \*Be sure to follow manufacturer's safety precautions and directions for use when using solvents.

• Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory

### **Storage and Shelf Life**

Store under normal conditions of 70°F (21°C) and 50% relative humidity. To obtain best performance, use product within 24 months from date of manufacture.

#### **Industry Specifications**

MIL-P-19834B, Type I

#### Trademarks

3M is a trademark of 3M Company.

#### References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M- Adhesive-Transfer-Tape-463?N=5002385+3293241524&rt=rud
	https://www.3m.com/3M/en_US/company-us/SDS-search/results/? gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=463

## 3M<sup>™</sup> Adhesive Transfer Tape 463

## **Family Group**

	463	465	9457	9665
Liner Color Attribute Modifier: Primary	Tan, No Print	Tan, No Print	White, No Print	Tan, No Print
Adhesive Thickness (mm)	0.05	0.05	0.025	0.05
Liner	60# Densified Kraft	60# Densified Kraft	55# Densified Kraft	60# Polycoated Kraft
Liner Thickness (mm)	0.09	0.09	0.08	0.11

#### **ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

#### **For Additional Information**

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/adhesives. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00

#### **Recognition/Certification**

TSCA: This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements

SDS: 3M has not prepared a SDS for this product which is not subjected to the SDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, this product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards.

UL: These products have been recognized by Underwriters Laboratories, Inc. under UL 969, Marking and Labeling Systems Materials Component. For more information on the UL Certification, please visit the website at http://www.3M.com/converter, select UL Recognized Materials, then select the specific product area.

#### Military: Meets Mil-P 19834B Type 1.

Note: One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at 3M.com/regs.

### 3M<sup>™</sup> Adhesive Transfer Tape 463

#### Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



3M United States 3M Center St. Paul, MN 55144-1000 800-362-3550 www.3M.com