

February, 2008

## 3M™ Ultra High Temperature 100 HT Adhesive Transfer Tape 9082

### Product Description

3M™ Ultra High Temperature 100HT Adhesive Transfer Tape 9082 utilizes a high performance and low outgassing adhesive system having excellent heat resistance in high temperature environments. Not only does it have excellent holding power, but also its adhesion strength is significantly higher than typical pressure sensitive tapes.

This adhesive transfer tape is ideal for use in many industrial applications subjected to higher temperature environments. Typical examples are for automotive under-hood applications that require both higher processing and operating temperatures. Other areas include printed circuit boards and heat sink bonding in many electronics applications subjected to high solder reflow temperatures.



**Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

**Typical Physical Properties**

Property	Values		Attribute Modifier
Color	Clear		
Adhesive Type	Acrylic Adhesive System		
Adhesive Thickness	0.05 mm	2 mil	
Density	0.98 g/cm <sup>3</sup>	0.04 lb/in <sup>3</sup>	
Liner	55# Densified Kraft		
Liner Color	White, with green “3M” print		Primary
Liner Thickness	0.08 mm	3.2 mil	

**Typical Performance Characteristics**

180° Peel Adhesion		Temp C	Temp F	Dwell/Cure Time
8.8 N/cm	80 oz/in	23C	73F	
7 N/cm	64 oz/in	107C	225F	
6.1 N/cm	56 oz/in	149C	300F	
5.3 N/cm		177C	350F	
48 oz/in		177C	350F	Initial
2.6 N/cm	24 oz/in	230C	450F	Initial

Property: 180° Peel Adhesion

Method: ASTM D3330

Backing: 2 mil Aluminum Foil

notes: Both tapes made from the same adhesive system and are thermoplastic in nature, becoming softer as temperature increases and firmer as temperature decreases. As the adhesive becomes firmer, the adhesion performance generally increases. At low temperatures (lower than -40°F [-40°C]), the tapes become very firm and glassy; the ability to absorb impact energy is reduced. In contrast, adhesion strength reduces with increasing temperatures. Typical adhesive strength properties at different temperatures are shown below. (Note: Samples were conditioned at the desired temperature for two minutes before testing at that temperature.)

Normal Tensile		Test Condition
345 kPa	50 lb/in <sup>2</sup>	Room Temperature
100 kPa	15 lb/in <sup>2</sup>	@ 225°F(107°C)
100 kPa	15 lb/in <sup>2</sup>	@ 300°F(149°C)
70 kPa	10 lb/in <sup>2</sup>	@ 350°F(177°C)

Table continued on next page

**Typical Performance Characteristics (continued)**

Normal Tensile		Test Condition
70 kPa	10 lb/in <sup>2</sup>	@ 450°F(230°C)

Property: Normal Tensile  
 Method: ASTM D897  
 Attribute Modifier: T-Block  
 Substrate: Aluminum

notes: Both tapes made from the same adhesive system and are thermoplastic in nature, becoming softer as temperature increases and firmer as temperature decreases. As the adhesive becomes firmer, the adhesion performance generally increases. At low temperatures (lower than -40°F [-40°C]), the tapes become very firm and glassy; the ability to absorb impact energy is reduced. In contrast, adhesion strength reduces with increasing temperatures. Typical adhesive strength properties at different temperatures are shown below. (Note: Samples were conditioned at the desired temperature for two minutes before testing at that temperature.)

Relative High Temperature Operating Ranges		Test Condition
280 °C	540 °F	Short Term (minutes, hours)
177 °C	350 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

Static Shear	Test Condition
1000 g	Hold weight listed @ Room Temperature for 10,000 min
1000 g	Hold weight listed @ 93°C (200°F) for 10,000 min
1000 g	Hold weight listed @ 121°C (250°F) for 10,000 min
1000 g	Hold weight listed @ 150°C (300°F) for 10,000 min
1000 g	Hold weight listed @ 175°C (350°F) for 10,000 min

Property: Static Shear  
 Method: ASTM D3654  
 Substrate: Aluminum

notes: Both tapes made from the same adhesive system and are thermoplastic in nature, becoming softer as temperature increases and firmer as temperature decreases. As the adhesive becomes firmer, the adhesion performance generally increases. At low temperatures (lower than -40°F [-40°C]), the tapes become very firm and glassy; the ability to absorb impact energy is reduced. In contrast, adhesion strength reduces with increasing temperatures. Typical adhesive strength properties at different temperatures are shown below. (Note: Samples were conditioned at the desired temperature for two minutes before testing at that temperature.)

Overlap Shear Strength		Test Condition
620 kPa	90 lb/in <sup>2</sup>	Room Temperature
240 kPa	35 lb/in <sup>2</sup>	@ 225°F(107°C)
210 kPa	30 lb/in <sup>2</sup>	@ 300°F(149°C)
140 kPa	20 lb/in <sup>2</sup>	@ 350°F(177°C)
100 kPa	15 lb/in <sup>2</sup>	@ 450°F(230°C)

Property: Overlap Shear Strength  
 Method: ASTM D1002  
 Substrate: Stainless Steel

notes: Both tapes made from the same adhesive system and are thermoplastic in nature, becoming softer as temperature increases and firmer as temperature decreases. As the adhesive becomes firmer, the adhesion performance generally increases. At low temperatures (lower than -40°F [-40°C]), the tapes become very firm and glassy; the ability to absorb impact energy is reduced. In contrast, adhesion strength reduces with increasing temperatures. Typical adhesive strength properties at different temperatures are shown below. (Note: Samples were conditioned at the desired temperature for two minutes before testing at that temperature.)

# 3M™ Ultra High Temperature 100 HT Adhesive Transfer Tape 9082

## Available Sizes

Property	Values	
Note	Subject to Minimum Order Requirements	
Standard Roll Length	54.9 m	60 yd
Normal Slitting Tolerance	± 0.8 mm	± 1/32 in

Maximum Length		Width
54.9 m	60 yd	1/2 in width
110 m	120 yd	1/2 in to 1 in widths
110 m	120 yd	1 in to 3 in
165 m	180 yd	3 in and wider

Property: Maximum Length

## Electrical and Thermal Properties

Property	Values		Method
Insulation Resistance	$>1 \times 10^6$ M $\Omega$ /in <sup>2</sup>		ASTM D1000
Thermal Conductivity	0.16 W/m/K	1.1 (btu-in)/(h-ft <sup>2</sup> -°F)	ASTM C177

Dielectric Strength	Test Condition
1200 V	Room Temperature
870 V	125°C
770 V	175°C

Property: Dielectric Strength  
Method: ASTM D149

## Additional Typical Performance Characteristics

**Coefficient of Thermal Expansion:**  $770 \times 10^{-6}$  m/m/°C

**Weight Loss and Outgassing Performance**

Property	Values	Test Condition	Notes
Isothermal TGA Analysis	0.64 %	@ 300°F (149°C)	The testing is done using a constant temperature Thermogravimetric Analysis (TGA). Samples were analyzed by tested in a TA Instruments 2950 HI-RES Modulated Thermogravimetric running under air atmosphere in standard mode. The sample temperature was increased from ambient to the desired temperature using the instruments highest heating rate and maintained at that temperature for 3.5 hours. Results are reported as percent weight loss based on the original weight of the sample.
Isothermal TGA Analysis	1.09 %	@ 350°F (177°C)	The testing is done using a constant temperature Thermogravimetric Analysis (TGA). Samples were analyzed by tested in a TA Instruments 2950 HI-RES Modulated Thermogravimetric running under air atmosphere in standard mode. The sample temperature was increased from ambient to the desired temperature using the instruments highest heating rate and maintained at that temperature for 3.5 hours. Results are reported as percent weight loss based on the original weight of the sample.

Ramped TGA Analysis	Test Condition
0.15 %	@ 225°F (107°C)
0.21 %	@ 300°F (149°C)
0.26 %	@ 350°F (177°C)

Table continued on next page

## Weight Loss and Outgassing Performance (continued)

Ramped TGA Analysis	Test Condition
0.61 %	@ 450°F (230°C)
1 %	@ 500°F (260°C)
5 %	@ 585°F (307°C)

Property: Ramped TGA Analysis

notes: The testing is done using a constant temperature Thermogravimetric Analysis (TGA). Samples were analyzed by tested in a TA Instruments 2950 HI-RES Modulated Thermogravimetric running under air atmosphere in standard mode. The sample temperature was increased from ambient to a high temperature above 1,000°F (537°C) at a rate of 10°C per minute. Results are reported as percent weight loss at the desired temperature points based on the original weight of the sample.

## Handling/Application Information

### Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry, and well unified. Some typical surface cleaning solvents are isopropyl alcohol/water mixture or heptane.\*

Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

\*Note: Be sure to follow the manufacturer's precautions and directions for use when using solvents.

### Storage and Shelf Life

Store in original cartons at 70°F (21°C) and 50% relative humidity.

If stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.

### Trademarks

3M is a trademark of 3M Company.

### References

Property	Values
3m.com Product Page	<a href="https://www.3m.com/3M/en_US/company-us/all-3m-products/-/3M-Ultra-High-Temperature-Adhesive-Transfer-Tape-9082?N=5002385+3293241972&amp;rt=rud">https://www.3m.com/3M/en_US/company-us/all-3m-products/-/3M-Ultra-High-Temperature-Adhesive-Transfer-Tape-9082?N=5002385+3293241972&amp;rt=rud</a>
Safety Data Sheet (SDS)	<a href="https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=9082">https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=9082</a>

# 3M™ Ultra High Temperature 100 HT Adhesive Transfer Tape 9082

## Family Group

	9082	9085	9085UV
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	280	280	280
Liner Color Attribute Modifier: Primary	White, with green "3M" print	White, with green "3M" print	Brown
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	177	177	177
Color	Clear	Clear	Clear
Adhesive Type	Acrylic Adhesive System	Acrylic Adhesive System	Acrylic Adhesive System
Adhesive Thickness (mm)	0.05	0.13	0.13
Liner	55# Densified Kraft	55# Densified Kraft	58# Polycoated Kraft
Liner Thickness (mm)	0.08	0.08	0.1

## ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

