

March, 2007

3M™ High Performance Double Coated Tape 9087

Product Description

3M™ Double Coated Tapes with 3M™ Adhesive 375 provides a high level of adhesive peel and shear performance. The adhesive system used on these products provides good adhesion to both high and low surface energy substrates. The excellent initial tack ensures that a bond of good integrity is achieved soon after application.



3M™ High Performance Double Coated Tape 9087

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Attribute Modifier
Color	White		
Total Tape Thickness without liner	0.26 mm	10.2 mil	
Carrier Thickness	0.038 mm	1.5 mil	
Adhesive	Modified Acrylic		
Adhesive Carrier	PVC		
Liner	Paper (Glassine)		
Liner Color	White with Green 3M Logo		Primary
Liner Thickness	0.07 mm	3 mil	

Typical Performance Characteristics

Relative High Temperature Operating Ranges		Test Condition
85 °C	185 °F	Short Term (minutes, hours)
70 °C	158 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

180° Peel Adhesion		Substrate
16 N/cm	146 oz/in	ABS
16 N/cm	142 oz/in	Stainless Steel
16 N/cm	146 oz/in	Polycarbonate (PC)
18 N/cm	164 oz/in	Glass
9 N/cm	82 oz/in	High Density Polyethylene (HDPE)
13 N/cm	119 oz/in	High Pressure Laminate

Property: 180° Peel Adhesion

Method: ASTM D3330

Attribute Modifier: Faceside

Dwell/Cure Time: 72

Dwell Time Units: hr

Temp C: 22C

Temp F: 72F

Environmental Condition: 52%RH

Backing: Aluminum Foil

notes: 12 in/min (300 mm/min)

Typical Performance Characteristics (continued)

Property	Values	Method	Test Condition	Notes
Static Shear	10000 min	ASTM D3654	1000 g @ Room Temperature	1 in ² sample size
Static Shear	10000 min	ASTM D3654	500 g @ 70°C (158°F)	1 in ² sample size
Solvent Resistance	Good			
UV Resistance	Excellent			
Plasticizer Resistance	Good			All products show good resistance to plasticizer migration. However due to the wide range of plasticizers available we strongly suggest that an evaluation is conducted prior to use to ensure compatibility. Sampling substrates with tape applied for 10 days at 158°F (70°C) will usually accelerate any potential problems. Plasticizers are typically found in materials such as polyvinyl chloride and some rubber products.

Handling/Application Information

Application Ideas

- POP Displays
- Plastic Extrusions
- Metal Fabrication
- Blister Packs and Packaging
- Sports Equipment
- Badge and Nameplates
- Indoor/Outdoor Signs
- Fabric and Leather Stitching
- Blind Manufacturers
- Print Finishing
- Furniture Trim
- Splicing

Storage and Shelf Life

Store in original carton at 70°F (21°C) and 50% relative humidity.
 If stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.

Trademarks

3M is a trademark of 3M Company.

3M™ High Performance Double Coated Tape 9087

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/-/3M-High-Performance-Double-Coated-Tape-9087?N=5002385+3293241868&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9087

Family Group

	9086	9087	9088 to 200	9088F200
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	120	85		
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	85	70		
Liner Color Attribute Modifier: Primary	White with Black 3M Logo	White with Green 3M Logo		Red
Color	Translucent	White		
Total Tape Thickness without liner (mm)	0.019	0.26	0.2	0.2
Carrier Thickness (mm)		0.038	0.012	0.012
Adhesive	Modified Acrylic	Modified Acrylic		
Adhesive Carrier	Tissue	PVC	PET (Polyester)	PET (Polyester)
Liner	Paper (Glassine)	Paper (Glassine)	58# Glassine	Polypropylene Film
Liner Thickness (mm)	0.07	0.07	0.08	0.08

ISO Statement

This product was manufactured under a quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

