

July, 2006

3M™ Double Coated Tape 9443NP

Product Description

3M™ Double Coated Tapes with 3M™ Synthetic Rubber Adhesive 700 Series feature a high tack synthetic rubber adhesive which provides excellent quick stick or initial adhesion and bonds together a wide variety of materials such as metals, papers, paints and most plastics. These tapes have a film carrier, which can add dimensional stability for aid in removal and also provides easier handling during slitting and die-cutting.

Product Features

- The high density polyethylene carrier in these products is hand-tearable, and provides dimensional stability and improved handling with ease of die-cutting and lamination compared to adhesive transfer tapes.
- 3M™ Adhesive 700 provides high tack adhesion to a variety of substrates, including metals, plastics and glass.
- 3M™ Adhesive 700 provides clean removal from many surfaces.
- Tape components are in compliance with Title 21 of the code of Federal Regulations (21 CFR) as indirect food additives.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Attribute Modifier	Notes
Color	Clear			
Tape Thickness	0.15 mm	6 mil		
Carrier Thickness	0.051 mm	2 mil		
Adhesive Type	700 Synthetic Rubber		Faceside	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.
Adhesive Type	700 Synthetic Rubber		Backside	Backside adhesive is on the exterior of the roll, exposed when liner is removed.
Adhesive Carrier	HDPE (High Density Polyethylene)			
Liner	60# Densified Kraft			
Liner Color	Green Plaid, no print		Primary	
Liner Thickness	0.1 mm	4 mil		

Adhesive Thickness		Attribute Modifier	Notes
0.051 mm		Backside	The caliper listed is based on a calculation from manufacturing controlled adhesive coat weight. While past data pages have listed nominal thicknesses of 1 and 2 mils, the coat weight (and theoretical caliper) has not changed.
2 mil		Backside	Backside adhesive is on the exterior of the roll, exposed when liner is removed.
0.051 mm	2 mil	Faceside	Faceside adhesive is on the interior of the roll, exposed when unwound and liner removed.

Property: Adhesive Thickness

Typical Performance Characteristics

90° Peel Adhesion		Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Substrate	Backing	Notes
10.1 N/cm		15	min	22C	72F	Stainless Steel	2 mil Aluminum Foil	
93 oz/in		15	min	22C	72F	Stainless Steel	2 mil Aluminum Foil	12 in/min (300 mm/min)
10.6 N/cm	97 oz/in	72	hr	22C	72F	Stainless Steel	2 mil Aluminum Foil	12 in/min (300 mm/min)
13.7 N/cm	126 oz/in	72	hr	70C	158F	Stainless Steel	2 mil Aluminum Foil	12 in/min (300 mm/min)
9.3 N/cm	85 oz/in	72	hr	22C	72F	Polypropyler (PP)	e2 mil Aluminum Foil	12 in/min (300 mm/min)
11 N/cm	101 oz/in	72	hr	22C	72F	Polycarbona (PC)	e2 mil Aluminum Foil	12 in/min (300 mm/min)
9.7 N/cm	89 oz/in	72	hr	22C	72F	Polyester (PET)	Aluminum Foil	

Property: 90° Peel Adhesion Method: ASTM D3330 Environmental Condition: 52%RH

Relative High Temperature Operating Ranges		Test Condition
70 °C	158 °F	Short Term (minutes, hours)
49 °C	120 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

Property	√ Values		Metho	Test dCondi	ti òlo tes	Dwell/ Time	Dwell Türree Units	Temp C	Temp F		nmenta ti 6a bsti	al ra Be cking
Static Shear	10000 min		ASTM D3654	g @ I Room	0.5 in² sample size rature							
Static Shear	17 min		ASTM D3654	g @	0.5 in² sample size							
180° Peel Adhesion	22.4 N/cm	206 oz/in	ASTM D3330		12 in/min (300 mm/min)	72	hr	22C	72F	52%RI	HStainle Steel	s A luminun Foil

Available Sizes

Property	Values		Attribute Modifier
Standard Roll Length	33 m	36 yd	
Minimum Available Width	6.35 mm	1/4 in	
Maximum Available Width	660 mm	26 in	
Normal Slitting Tolerance	±0.8 mm	±1/32 in	
Core Size	76.2 mm	3 in	ID

Maximum Length		Width	
329 m	360 yd	1/2 in(12.7mm) and wider	
165 mm	180 yd	1/4 to 7/16 in	

Property: Maximum Length

Handling/Application Information

Application Ideas

- Miscellaneous joining and holding uses where high initial tack is required.
- Quick and easy tacking of carpet edges.
- General industrial mounting, joining and splicing.

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength. To obtain optimum adhesion, the bonding surfaces must

be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*

*Note: Carefully read and follow the manufacturer's precautions and directions for use when working with solvents.

Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

Application Equipment

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, Lamination Techniques for Converters of Laminating Adhesives (70-0704-1430-8). For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

Storage and Shelf Life

Store in original cartons at 70°F (21°C) and 50% relative humidity.

When stored under proper conditions, product retains its performance and properties for 18 months from date of manufacture.

Industry Specifications

Title 21 of the code of Federal Regulations (21 CFR)

References

Property	Values
	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M- Double-Coated-Tape-9443NP?N=5002385+3293240979&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/? gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9443NP

Family Group

	9443NP	9589	9579
Adhesive Type Attribute Modifier: Faceside	700 Synthetic Rubber	760 Synthetic Rubber	760 Synthetic Rubber
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	70	70	66
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	49	49	49
Adhesive Thickness (mm) Attribute Modifier: Backside	0.051	0.076	0.076
Liner Color Attribute Modifier: Primary	Green Plaid, no print	Green Plaid, no print	White, no print
Adhesive Type Attribute Modifier: Backside	700 Synthetic Rubber	760 Synthetic Rubber	760 Synthetic Rubber
Adhesive Thickness (mm) Attribute Modifier: Faceside	0.051	0.076	0.076
Color	Clear	White	White
Tape Thickness (mm)	0.15	0.23	0.127
Carrier Thickness (mm)	0.051	0.076	0.076
Adhesive Carrier	HDPE (High Density Polyethylene)	HDPE (High Density Polyethylene)	HDPE (High Density Polyethylene)
Liner	60# Densified Kraft	60# Densified Kraft	White 62# Densified Kraft
Liner Thickness (mm)	0.1	0.1	0.1

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Recognition/Certification

FDA

The components in 3M™ Double Coated Tapes 9443NP and 9589 are in compliance with the requirements for use as indirect food additives under Title 21 of the Code of Federal Regulations (21 CFR). The carrier material is regulated under 21 CFR 177.1520 (c) (3.1) and (3.2) (Olefin polymers). All of the adhesive components are regulated under 21 CFR 175.105 (Adhesives). As found in 21 CFR 175.105, there are usage restrictions associated with all adhesives used around food. As indicated in this regulation, the adhesive must either be separated from the food by a functional barrier or used subject to the following:

- (1) In dry foods: used such that the quantity of adhesive that contacts the packaged dry food does not exceed the limits of good manufacturing practice.
- (2) In fatty and aqueous foods: the quantity of adhesive that contacts the packaged fatty and aqueous food does not exceed the trace amount at the seams and at the edge exposure between packaging laminates that may occur within the limits of good manufacturing practice.
- It is the responsibility of the end user to ensure that his or her application is in compliance with these usage restrictions.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

