

2019-11-01 00:00:00

3M[™] Adhesive Transfer Tape 9773WL

Product Description

Finite Element Analysis (FEA) data is available for this product at: 3m.com/FEA

3M[™] Adhesive Transfer Tape 9773WL with 3M[™] Adhesive 300MP is suitable for bonding to most surfaces. The acrylic adhesive provides an excellent bond to various fabricated foams, fabrics, substrates, and has good shear strength at elevated temperatures. This tape also meets the highly variable needs of most gasket fabricators.



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Method	Attribute Modifier
Total Tape Thickness	0.076 mm	0.003 in	ASTM D3652	
Adhesive Type	300MP Acrylic Adhesive			
Adhesive Thickness	0.076 mm	3 mil		
Liner	96# Polycoated Kraft Paper			
Liner Color	White			Primary
Liner Thickness	0.18 mm	7 mil		

Typical Performance Characteristics

90° Peel Adhesion			Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Substrate	Backing
4.06 lb/in	7.2 N/cm	65 oz/in	72	hr	22C	72F	52%RH	Stainless Steel	2 mil Aluminum Foil
6.6 N/cm	59 oz/in		15	min	22C	72F	52%RH	ABS	2 mil Aluminum Foil
3.7 N/cm	33 oz/in		15	min	22C	72F	52%RH	Polypropylene (PP)	2 mil Aluminum Foil
13.6 N/cm	122 oz/in		72	hr	70C	158F	52%RH	Stainless Steel	2 mil Aluminum Foil
5 N/cm	45 oz/in	3.69 lb/in	72	hr	22C	72F	52%RH	ABS	2 mil Aluminum Foil
4.1 N/cm	37 oz/in		72	hr	22C	72F	52%RH	Polypropylene (PP)	2 mil Aluminum Foil
10 N/cm	90 oz/in		72	hr	38C	100F	100%RH	Stainless Steel	2 mil Aluminum Foil
6.8 N/cm	61 oz/in		72	hr	70C	158F	52%RH	Polypropylene (PP)	2 mil Aluminum Foil

Table continued on next page

3M[™] Adhesive Transfer Tape 9773WL

Typical Performance Characteristics (continued)

90° Peel Adhesion		Dwell/Cure Time	Dwell Time Units	Temp C	Temp F	Environmental Condition	Substrate	Backing
5 N/cm	45 oz/in	72	hr	70C	158F	52%RH	ABS	2 mil Aluminum Foil
2.06 lb/in		72	hr	22C	72F	52%RH	Polypropylene (PP)	2 mil PET

Property: 90° Peel Adhesion Method: ASTM D3330 notes: 12 in/min (300 mm/min)

Static Shear	Test Condition	Substrate	Notes	Dwell/Cure Time
10000 g	Room Temperature	Stainless Steel	Tested at various temperatures and gram loadings. 0.5 in² (3.23 cm²). Will hold listed weight for 10,000 minutes (approximately 7 days).	
10000 min	1000 g @ Room Temperature		1" x 1" Overlap	60 min
10000 min	250 g @ 70°C (158°F) high temperature shears		1" x 1" Overlap	60 min

Property: Static Shear Method: ASTM D3654

Property	Values		Notes	Test Condition
Short Term Temperature Resistance	121 °C	250 °F	No change in room temperature dynamic shear properties following 4 hours conditioning at indicated temperature with 100 g/static load. (Represents minutes, hours in a process type temperature exposure).	
Relative High Temperature Operating Ranges	121 °C	250 °F		Short Term (minutes, hours)
UV Resistance	Adhesive is resistant to oxidation and ozone when exposed to air or ultraviolet light.			

3M[™] Adhesive Transfer Tape 9773WL

Available Sizes

Property	Values		Attribute Modifier
Standard Roll Length	180 yd		
Maximum Available Width	60 in		
Normal Slitting Tolerance	± 1/32 in		
Core Size	75 mm	3 in	ID

Typical Environmental Performance

Humidity Resistance

No adverse effect on the bond after exposure to 100% relative humidity at 100°F (38°C)

Storage and Shelf Life

Store in the original packaging at room temperature conditions of 72°F (22°C) and 50% relative humidity. Keep out of direct sunlight. Product retains its performance properties for 24 months from date of manufacture.

Trademarks

3M is a trademark of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M- Adhesive-Transfer-Tape-9773WL?N=5002385+3293240968&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/? gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9773WL

Family Group

	9772WL	9773WL	9774WL	9775WL
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	121	121	121	121
Liner Color Attribute Modifier: Primary	White	White	White	White
Total Tape Thickness (mm)	0.05	0.076	0.101	0.127
Adhesive Type	300MP Acrylic Adhesive	300MP Acrylic Adhesive	300MP Acrylic Adhesive	300MP Acrylic Adhesive

Table continued on next page

3M[™] Adhesive Transfer Tape 9773WL

Family Group (continued)

	9772WL	9773WL	9774WL	9775WL
Adhesive Thickness (mm)	0.051	0.076	0.102	0.127
Liner	96# Polycoated Kraft Paper			
Liner Thickness (mm)	0.18	0.18	0.18	0.18

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



3M United States 3M Center St. Paul, MN 55144-1000 800-362-3550 www.3M.com