

June, 2009

3M™ General Purpose Double-Coated Tape 9817L

Product Description

3M™ General Purpose Double-Coated Tape 9817L provides a balance of peel and shear properties with good heat resistance. Immediate bond utilizing only normal nip pressure when laminated to most open cell urethane and closed cell urethane foams.

It bonds well to polyester, polyester urethane, polyethylene, polystyrene, vinyl foams and most rubbers. Exposed side is acrylic, liner side is rubber-based. Excellent quick stick and adhesion to high and low energy surfaces.



Product Features

- Extremely high-bond strength to most surfaces.
- Excellent versatility for lamination to foam material.
- Excellent dimensional stability with polyester carrier.
- Densified Kraft liner for rotary die-cutting.
- Good rotary die-cutting characteristics from the super calendared kraft liner.
- Use where high heat or UV resistance is not required.

3M™ General Purpose Double-Coated Tape 9817L

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values
Total Tape Thickness without liner	3.3 mil
Adhesive Carrier	Polyester Film
Liner	60# Kraft
Relative Adhesion (HSE)	High
Relative Adhesion (LSE)	Medium

Typical Performance Characteristics

	Test Condition
	Short Term (minutes, hours)
	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

180° Peel Adhesion		Temp C	Temp F	Substrate	Backing
2.3 N/cm	21 oz/in	22C	72F	Polypropylene (PP)	
6.6 N/cm	60 oz/in	22C	72F	Stainless Steel	
10.5 N/cm	96 oz/in	22C	72F	Neoprene Rubber	2 mil Polyester Film
4.5 N/cm	41 oz/in	70C	158F	Neoprene Rubber	2 mil Polyester Film

Property: 180° Peel Adhesion
 Method: ASTM D3330
 Dwell/Cure Time: 72
 Dwell Time Units: hr
 Environmental Condition: 52%RH
 notes: 12 in/min (300 mm/min)

Property	Values	Method	Dwell/Cure Time	Test Condition	Notes
Static Shear	10000 min	ASTM D3654	60 min	1000 g @ Room Temperature	1" x 1" Overlap
Static Shear	4000 min	ASTM D3654	60 min	250 g @ 70°C (158°F) high temperature shears	1" x 1" Overlap
Solvent Resistance	Medium				

3M™ General Purpose Double-Coated Tape 9817L

Environmental Resistance

Properties defined are based on the adhesion of impervious faceplate materials to a stainless steel test surface.

Bond Build Up: The adhesive bond increases as a function of time and temperature.

Heat Resistance: 3M tape 9816L,M,H 150°F (65°C)

3M tape 9817L,M,H Acrylic-220°F (105°C) Rubber-175° (80°C)

Low Temp. Resistance: 40°F (4.4°C).

Processing

Die-cutting: Good die-cuttability. Lubricate dies with vanishing oil or similar low lubricants for improved processing.

Roll Laminating: Use rubber over steel roll set up with moderate application pressure. Make adhesive to substrate contact at nip area only.

Handling/Application Information

Application Ideas

- General purpose foam or rubber laminating (60 in).
- General purpose lamination of fabricated parts.

Application Techniques

For maximum bond strength, surface should be thoroughly cleaned and dried. A typical cleaning solvent is heptane or isopropyl alcohol. When using cleaning solvents, vanishing oils, or lubricants, consult the manufacturer's Material Safety

Data Sheet for proper handling and storage instructions.

Bond strength may be improved with firm application pressure and moderate heat causing adhesive to flow and develop intimate contact with bonding surface.

This adhesive is good for most indoor applications and can be used for outdoor applications if the adhesive is not directly exposed to the environment.

The temperature resistance is somewhat lower than our typical acrylics. Therefore, temperatures above 150°F (65°C) should be avoided.

Avoid contact with plasticized vinyl or plasticized rubber surfaces. Plasticizers will soften the rubber adhesive.

Storage and Shelf Life

Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.

If stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.

Trademarks

3M is a trademark of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~/-/3M-Double-Coated-Tape-9817L?N=5002385+3291148961&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9817L

3M™ General Purpose Double-Coated Tape 9817L

Family Group

	9816L	9816M	9816H	9817L	9817M	9817H
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	65	65	65	Acrylic: 105	Acrylic: 105	Acrylic: 105
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	49	49	49	Acrylic: 80	Acrylic: 80	Acrylic: 80
Adhesive Carrier	Polyester Film	Polyester Film	Polyester Film	Polyester Film	Polyester Film	Polyester Film
Liner	60# Kraft	74# Kraft	14 pt board	60# Kraft	74# Kraft	14 pt board

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

