
# FT 1943 PP

Avery Dennison™ FT 1943 PP is a 4 mil transfer tape with a LSE modified acrylic adhesive that offers extremely high adhesion to low surface energy materials while providing excellent environmental resistance.

#### **FEATURES**

- Aggressive modified acrylic adhesive
- Tear resistant liner
- · Moisture resistant release liner



### **BENEFITS**

- Excellent die-cutting characteristics
- Heavy adhesive mass for bonding to irregular of rough surfaces
- Good solvent resistance
- Strong polypropylene release liner
- Two-year warranty

# **CONSTRUCTION:**

Liner:

4 mil White Polypropylene

Adhesive:

LSE Modified Acrylic



#### FT 1943 PP

Adhesive Properties:		Typical Values		
Thickness	ASTM D3652	US Mils	MM's	Micron's (μm)
Liner		4.0	0.10	102
Adhesive		4.0	0.10	102
Total Caliper without Liner	•	4.0	0.10	102
Total Caliper:		8.0	0.20	203
Peel Adhesion	ASTM D3330			
180° 12 in (300 mm) min	@ Room Temp	1 166 / 300		N. / Mater
Substrate	70 ha shorall	Lbf / in 10.6		<b>N / Meter</b> 1,867
SS	72 hr dwell	10.6		1,867
	+			
ABS	72 hr dwell	10.4		1,831
100	72 III GWOII	10.7		1,001
PP	72 hr dwell	10.5		1,849
Loop Tack	ASTM D6195			
180° 32 in (508 mm) / mi	n @ Room Temp			
Substrate	T	Lbf / in		N / Meter
SS	Initial	10.0		1,761
		l		
Static Shear	ASTM D3654			
	00 g @ Room Temp			
Substrate	oo g & Room Temp	Min to Fail		
SS	Liner 24 hr dwell	> 10,000		
-		. 10,000		
	l .	I .	I	
TEMPERATURES		۰F		° C
Minimum Anniliantia T				100 0

350° F
THE LISTED VALUES ARE TYPICAL AND NOT INTENDED TO SERVE AS PRODUCT SPECIFICATIONS

50° F

-40° F

# **APPLICATION TECHNIQUES**

Maximum Service Temperature

Minimum Application Temperature
Minimum Service Temperature

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

## STORAGE / SHELF LIFE

• Two years when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison.com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2020 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.

Europe



Performance Tapes Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

China, 215335 Phone: +86 512 57155001 Fax: +86 512 57155059 Tieblokkenlaan 1 B-2300 Turnhout Belgium Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55 North America 250 Chester Street Painesville, Ohio 44077 USA

10° C

-40° C

175° C

Phone: +1 866-462-8379 Fax: +1 888-358-4469